



# PLACER COUNTY

## APCD Rule 234

Effective July 1, 2011

Product	Mix Ratio	Hardener	Activator / Reducer	Additive	Applied VOC	
<b>Pretreatment Coating</b>					<b>System Limit: 660 g/L</b>	<b>VOC Regulatory</b>
Autoprep Etching Pen CF	Ready to use	N/A	N/A	N/A	0 g/L	
Autoprep Pretreatment Wipes	Ready to use	N/A	N/A	N/A	0 g/L	
Lesonal Self Etching Primer CF	1:1:1	Lesonal Self Etching Hardener CF LV	Lesonal Reducer LV	N/A	654 g/L	
<b>Primer (Surfacer)</b>					<b>System Limit: 250 g/L</b>	<b>VOC Regulatory</b>
LV HS Surfacer/Sealer	4:1:1	LV HS Surfacer / Sealer Hardener	LV HS Surfacer Activator	N/A	209 g/L	
	4:1 additive then 4:1:1	LV HS Surfacer / Sealer Hardener	LV HS Surfacer Activator	Lesonal Flex Additive	201 g/L	
	3:1 additive then 4:1:1	LV HS Surfacer / Sealer Hardener	LV HS Surfacer Activator	Lesonal Flex Additive	199 g/L	
Grey Urethane Surfacer	3:1:10%	Lesonal Urethane Surfacer Hardener LV	Lesonal Reducer LV	N/A	247 g/L	
<b>Primer (Sealer)</b>					<b>System Limit: 250 g/L</b>	<b>VOC Regulatory</b>
LV HS Surfacer/Sealer	100:25:35	LV HS Surfacer / Sealer Hardener	LV HS Sealer Activator	N/A	238 g/L	
	4:1 additive then 100:25:35	LV HS Surfacer / Sealer Hardener	LV HS Sealer Activator	Lesonal Flex Additive	229 g/L	
	3:1 additive then 100:25:35	LV HS Surfacer / Sealer Hardener	LV HS Sealer Activator	Lesonal Flex Additive	227 g/L	
<b>Color Coating (Basecoat)</b>					<b>System Limit: 420 g/L</b>	<b>VOC Regulatory</b>
Basecoat WB	100:0-40	N/A	Activator WB	N/A	417 g/L	
	100:5 hardener then 100:0-40 activator	WB Hardener	Activator WB	N/A	410 g/L	
	100:5 additive then 100:0-40 activator	N/A	Activator WB	Ready Mixed Additive	418 g/L	
<b>Clear Coating</b>					<b>System Limit: 250 g/L</b>	<b>VOC Regulatory</b>
Lesonal ProAir Clear LV	3:1:1	ProAir Clear LV Hardener	ProAir Clear LV Activators	N/A	222 g/L	
	5:1 additive then 3:1:1	ProAir Clear LV Hardener	ProAir Clear LV Activators	Lesonal Flex Additive	220 g/L	
Lesonal LV Clear	2:1:20%	LV Clear Hardener	LV Clear Reducers	N/A	246 g/L	
	4:1 additive then 2:1:20%	LV Clear Hardener	LV Clear Reducers	Lesonal Flex Additive	230 g/L	
Lesonal Mat LV	100:50:30	LV Clear Hardener	LV Clear Reducers	N/A	149 g/L	
	100:33 additive then 100:50:30	LV Clear Hardener	LV Clear Reducers	Lesonal Flex Additive	157 g/L	
<b>Surface Cleaners (max usage 20 gallons per year)</b>					<b>System Limit: 350 g/L</b>	<b>VOC Actual</b>
Plastic Surface Cleaner	Ready to Spray	N/A	N/A	N/A	756 g/L	
<b>Surface Cleaners (unlimited usage)</b>					<b>System Limit: 25 g/L</b>	<b>VOC Actual</b>
Autoclean Surface Cleaner	Ready to Spray	N/A	N/A	N/A	9 g/L	
<b>Gun Cleaners</b>					<b>System Limit: 25 g/L</b>	<b>VOC Actual</b>
Gun Cleaner WB	Ready to Spray	N/A	N/A	N/A	24 g/L	





# PLACER COUNTY

## APCD Rule 234

Effective July 1, 2011

Product	VOC Regulatory	VOC Actual
Autoprep Etching Pen CF	0	0
Autoprep Cleaning Wipes	0	0
Lesonal Self Etching Primer CF	625	621
LV HS Surfacer/Sealer	247	145
Grey Urethane Surfacer	178	133
Basecoat WB	411	146
Lesonal ProAir Clear LV	201	110
Lesonal LV Clear	308	201
Lesonal Mat LV	169	90
Lesonal Self Etching Hardener CF LV	768	192
LV HS Surfacer / Sealer Hardener	0	0
Lesonal Urethane Surfacer Hardener LV	467	333
WB Hardener	355	355
Lesonal ProAir Clear LV Hardener	0	0
LV Clear Hardener	113	68
Lesonal Reducer LV	159	1
LV HS Surfacer Activator	0	0
Lesonal Sealer Activator 2.1	512	106
Activator WB	885	10
Lesonal ProAir Clear LV Activator	803	268
LV Clear Reducers	0	0
Ready Mixed Additive	284	103
Lesonal Accelerator	800	800
Lesonal Flex Additive	198	164
Plastic Surface Cleaner	773	773
Autoclean Surface Cleaner	761	9
Gun Cleaner WB	942	24

